

BRONZI DA COLATA CONTINUA

Lega Alloy	Peso specifico Density	Composizione Chimica % Chemical Composition %	Indice di Lavorabilità Machinability (CuZn39Pb3=100)
CuSn7Zn4Pb7-C CC493K DIN EN 1982	8,8	Cu 81,0 - 85,0 Sn 6,0 - 8,0 Zn 2,0 - 5,0 Pb 5,0 - 8,0	85
CuSn12-C CC493K DIN EN 1982	8,8	Cu 81,0 - 85,0 Sn 6,0 - 8,0 Zn 2,0 - 5,0 Pb 5,0 - 8,0	70
CuSn11Pb2-C CC482K DIN EN 1982	8,9	Cu 83,5 - 87,0 Sn 10,5 - 12,5 Pb 0,7 - 2,5	70
CuSn12Ni2-C CC484K DIN EN 1982	8,6	Cu 84,5 - 87,5 Sn 11,0 - 13,0 Ni 1,5 - 2,5 P 0,05 - 0,40	70